

**GRIPTEK ANTI-SLIP SOLUTIONS PTY LTD** 

PO Box 150 Tullamarine 3043 VIC AUSTRALIA ABN: 13 622 802 797

T. 1300 01 GRIP E. info@griptek.com.au

Test Report No: 090921C

Slip Resistance Measurement of New Pedestrian Surfaces: AS4586:2013 Appendix A

Client: Volare Concepts - 5 Sharon Crt, Geelong North VIC 3215

**Test Date:** 9/09/2021 **Temperature:** 20 deg C.

Test Conducted to: AS 4586:2013 Appendix A Conducted by: Adam Dyson

**Test Method:** Wet Pendulum Testing **Test Device:** Munro S/N - 1509

Surface: Entiva Enzo Smart-Tech 20mm Rubber Slider Used: Slider 96 (4 S Rubber)

Slider Preparation: Abrasive paper, Grade P400 followed by pink lapping paper wet

Test Location: U 3/22-30 Wallace Ave, Point Cook VIC 3030

**Surface Preparation:** Cleaned with Water & Scrubbing

Surface Application: N/A.

## Tested Area:

Specimen Number	Location	Condition	Gradient %	Direction of Test	Mean BPN Last 3 swings
1	Loose Sample	As Found	<2.0	N/A	74
2	Loose Sample	As Found	<2.0	N/A	74
3	Loose Sample	As Found	<2.0	N/A	76
4	Loose Sample	As Found	<2.0	N/A	74
5	Loose Sample	As Found	<2.0	N/A	72

Mean BPN Slip Resistance Value - SRV 74

Classification P5

Contribution to Risk Very Low

Interpretation of the Wet Pendulum Results					
Classification of pedestrian surface materials according to the AS 4586	Mean BPN				
P5	>54				
P4	45-54				
P3	35-44				
P2	25-34				
P1	12-24				
P0	<12				

Approved Signatory: Michael Holt

The AS 4586 standard provides a guide & recommendation for use, we recommend that this report be read in conjuction with AS 4586 & Handbook HB198: 2014. Refer to Table 3B of HB 198 for requirements of sloped surfaces & ramps. The results in this test do not account for any future wear, contamination or maintenance of this surface. GripTek Anti-Slip Solutions Pty Ltd or our agents, licencees or employees accept no responsibility for any actions whatsoever which may arise as a result of this test report, all information within this report is copyright & is protected by copyright law.